

**Table 3.4.4 E: Formulation for Building Wire (NNM-B) Jacket**

<b>Material</b>	<b>Parts per Hundred Resin (PHR)</b>
PVC (electrical grade, medium MW)	100
DIDP (electrical grade)	55 – 60
CaCO <sub>3</sub>	50
Stearic acid	0.25
Calcium/zinc stabilizer	4 – 5
Epoxidized soybean oil (ESO)	0 - 5