

Table 3.4.4 G: Formulation for PVC Plenum Cables

Material	Parts per Hundred Resin (PHR)
PVC	100
ATH	60
FR plasticizer	40
Zinc borate	9
AOM	4.5
Antimony oxide	1
Antioxidant	0.2
Stearic acid	0.2
Calcium/zinc/zeolite stabilizer	4 - 6